

Test report n°: 20LA05895 of 08/05/2020





LAB N° 1165 L

Dear Frosio Bortolo Srl Via Nuova, 22/A 25070 Preseglie (BS)

## **Acceptance Data**

Subject of the test: Polymers

Transport: Customer

Date of arrival: 28/04/2020 Time of arrival: 11.00

Acceptance date: 28/04/2020





## Sample data

Description: CleanTouch Antibacterial protection

## Sampling data

Sampling by: Customer Place: Customer location

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.

Laboratory registered in the list of regional laboratories carrying out analysis in the context of self-control procedures for Food Industries No. 52. It is the responsibility of the OSA to communicate the warnings to the bodies in charge

Mod.PT01.01 Rev.9







LAB N° 1165 L

| Parameter - Specification  Method - Notes  | M.U. | Results<br>Notes                              | LoQ LoD | Test start<br>Test end   |
|--|------|---|---------|--------------------------|
| * Price emission test report in second language  |      |   |         | 06/05/2020               |
| Determination of antibacterial activity (R) - R=(Ut-Uo)-(At-Uo) ISO 22196:2011           |      | > 4.7   | 0,3     | 28/04/2020<br>30/04/2020 |
| Determination of antibacterial activity (R) ISO 22196:2011                               | %    | > 99.998                                      | 50      | 28/04/2020<br>30/04/2020 |
| Size of test specimens (H x L)   | mm   | 50x50   |         | 28/04/2020<br>30/04/2020 |
| Thickness of test specimens  | mm   | 2,0   |         | 28/04/2020<br>30/04/2020 |
| Type of polymer used for the cover film  |      | Polypropylene                                 |         | 28/04/2020<br>30/04/2020 |
| Size of the cover film (H x L)   | mm   | 40x40   |         | 28/04/2020<br>30/04/2020 |
| Thickness of the cover film  | mm   | 0,10  |         | 28/04/2020<br>30/04/2020 |
| Type of Gram-negative strain   |      | Escherichia coli<br>ATCC 8739                 |         | 28/04/2020<br>30/04/2020 |
| Method of conditioning   |      | UV-C radiation (30 min per side)              |         | 28/04/2020<br>30/04/2020 |
| Reference used   |      | Inert Internal<br>material<br>(polypropylene) |         | 28/04/2020<br>30/04/2020 |
| Volume of test inoculum  | ml   | 0,4   |         | 28/04/2020<br>30/04/2020 |
| Number of viable bacteria in the test inoculum   | n°   | 220000  |         | 28/04/2020<br>30/04/2020 |
| Uo - N° of viable bacteria recovered from the untreated test specimens after inoculation | log  | 4,1   | 0,4     | 28/04/2020<br>30/04/2020 |
| Ut - N° of viable bacteria recovered from the untreated test specimens after 24 h        | log  | 4,7   | 0,4     | 28/04/2020<br>30/04/2020 |
| At - Count bacteria recovered from the treated samples 24 hours post inoculation         | log  | NQ  | 0,4     | 28/04/2020<br>30/04/2020 |
|  |      |   |         |                          |

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.

Laboratory registered in the list of regional laboratories carrying out analysis in the context of self-control procedures for Food Industries No. 52. It is the responsibility of the OSA to communicate the warnings to the bodies in charge

Mod.PT01.01 Rev.9 Mod.PT01.01 Rev.9







LAB N° 1165 L

## Test report n°: 20LA05895 of 08/05/2020

| 20LA05895/01 CleanTouch Antibacte  | rial pro | otection                                      |         |                          |
|--|----------|---|---------|--------------------------|
| Parameter - Specification  Method - Notes  | M.U.     | Results<br>Notes                              | LoQ LoD | Test start<br>Test end   |
| Determination of antibacterial activity (R) - R=(Ut-Uo)-(At-Uo) ISO 22196:2011           |          | > 4.1   | 0,3     | 28/04/2020<br>01/05/2020 |
| Determination of antibacterial activity (R) ISO 22196:2011                               | %        | > 99.992                                      | 50      | 28/04/2020<br>01/05/2020 |
| Size of test specimens (H x L)   | mm       | 50x50   |         | 28/04/2020<br>01/05/2020 |
| Thickness of test specimens  | mm       | 2,0   |         | 28/04/2020<br>01/05/2020 |
| Type of polymer used for the cover film  |          | Polypropylene                                 |         | 28/04/2020<br>01/05/2020 |
| Size of the cover film (H x L)   | mm       | 40x40   |         | 28/04/2020<br>01/05/2020 |
| Thickness of the cover film  | mm       | 0,10  |         | 28/04/2020<br>01/05/2020 |
| Type of Gram-positive strain   |          | Staphylococcus<br>aureus - ATCC 6538          |         | 28/04/2020<br>01/05/2020 |
| Method of conditioning   |          | UV-C radiation (30<br>min per side)           |         | 28/04/2020<br>01/05/2020 |
| Reference used   |          | Inert Internal<br>material<br>(polypropylene) |         | 28/04/2020<br>01/05/2020 |
| Volume of test inoculum  | ml       | 0,4   |         | 28/04/2020<br>01/05/2020 |
| Number of viable bacteria in the test inoculum   | n°       | 140000  |         | 28/04/2020<br>07/05/2020 |
| Uo - N° of viable bacteria recovered from the untreated test specimens after inoculation | log      | 3,7   | 0,4     | 28/04/2020<br>07/05/2020 |
| Ut - N° of viable bacteria recovered from the untreated test specimens after 24 h        | log      | 4,1   | 0,4     | 28/04/2020<br>07/05/2020 |
| At - Count bacteria recovered from the treated samples 24 hours post inoculation         | log      | NQ  | 0,4     | 28/04/2020<br>01/05/2020 |

If the sampling is not the responsibility of 3ALaboratori srl, the latter declines all responsibility with regard to sampling information as provided by the Customer; the test results refer only to the sample as received. When these data include measurements that affect the measurement unit, the results expressed are obtained by processing them. The Acceptance Data is the responsibility of the Laboratory while the sample data are the responsibility of the Customer. If the sample is not suitable but the Customer chooses to continue anyway, the laboratory declines all responsibility for the results that could be influenced by the deviation

LEGEND: **U.M.** = Unit of measurement; **(Sup)** = upper limit; **(Inf)** = Lower Limit; **LoQ** = limit of quantification, it is the lower limit of concentration above which it is possible to obtain a quantitative measurement instrumentally; in microbiology the LoQ is of a theoretical nature; **LoD** = limit of detectability, is the lower limit of concentration below which the sample cannot be detected; in qualitative analyzes it represents the minimum concentration at which an analyte can be determined or not; **NQ** = unquantifiable, indicates a value less than LoQ; **NR** = not detectable, indicates a value lower than LoD;"<x" or ">x" respectively indicate a value lower or higher than the measuring range of the test, where x is the result

(§): Indicates a change from the previous version of the Test Report.

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.

Laboratory registered in the list of regional laboratories carrying out analysis in the context of self-control procedures for Food Industries No. 52. It is the responsibility of the OSA to communicate the warnings to the bodies in charge

Mod.PT01.01 Rev.9







LAB N° 1165 L

Test report n°: 20LA05895 of 08/05/2020

(le): Indicates that the parameters/activities are performed in subcontracting.

**UNLESS OTHERWISE SPECIFIED**: Quantitative microbiological tests are performed on single replica and two consecutive dilutions in accordance with UNI EN ISO 7218: 2013 (with the exception of the analysis of water and MPN); the results of this test report are not corrected for recovery factors (R) as the values of recovery are in the tolerance specified in the test method; summations are calculated using the criterion of the lower bound (LB)

(\*): Test/activity not accredited by ACCREDIA

| Technical Director   |
|--|
| Dr. Giovanni Mitaritonna<br>Chemist<br>Ordine Interprov. Chimici del Veneto - Padova nº 910 SEZ. A |
| End of Test Report   |

The analytical results are exclusively referred to the sample.

Representation of a Test Report signed electronically in accordance with current legislation.

This document can not be reproduced in part without the written permission of the laboratory.

Laboratory management system certified UNI EN ISO 9001: 2015 by CSQA with the No. 14270. Recommended by AIC for the analysis of quantification of gluten in food matrices. Registrated laboratory for the analysis of food contact materials intended for export to Japan.

Laboratory registered in the list of regional laboratories carrying out analysis in the context of self-control procedures for Food Industries No. 52. It is the responsibility of the OSA to communicate the warnings to the bodies in charge

Mod.PT01.01 Rev.9 Mod.PT01.01 Rev.9